

PROPIEDADES DE LA SECCIÓN DE ACERO: FY= 37000 LBS PLG 2 (2603 Kg/Cm²)

CALIBRE	ESPESOR ACERO BASE		PROPIEDADES EFECTIVAS			IX	PROPIEDADES SIN REDUCIR			
	Plg.	mm.	IX+	SX+	SX-		SX SUP.	SX INF.	AREA	Y INF.
			(Cm ⁴ /mt)	(Cm ³ /mt)	(Cm ³ /mt)	(Cm ⁴ /mt)	(Cm ³ /mt)	(Cm ³ /mt)	(Cm ² /mt)	(Cms)
24	0.0209	0.531	45.11	11.93	13.11	50.54	15.61	16.24	7.07	3.11
22	0.0299	0.759	69.54	19.22	20.66	72.31	22.32	23.23	10.12	3.11

LÁMINA LOSACERO

