

Espesor			Peso Teórico		Peso aproximado por hoja			
Calibre	Plg.	mm.	Kg/m ²	Kg/Pie ²	3' x 8'	3' x 10'	4' x 8'	4' x 10'
1/2"	0.5000	12.7	100.75	9.00	225.00	285.00	300.00	376.00
3/8"	0.3750	9.50	75.56	7.00	168.00	210.00	225.00	284.00
5/16"	0.3120	7.90	62.97	6.00	140.00	176.00	187.00	234.00
1/4"	0.2500	6.35	49.83	4.63	111.12	138.89	148.15	185.19
3	0.2390	6.07	48.82	4.54	108.85	136.07	145.14	181.42
4	0.2242	5.69	45.77	4.25	102.05	127.57	136.07	170.09
5	0.2090	5.31	42.72	3.97	95.25	119.06	127.00	158.75
6	0.1940	4.93	39.67	3.69	88.45	110.56	117.93	147.42
3/16"	0.1870	4.75	37.28	3.46	83.11	103.89	110.82	138.52
7	0.1790	4.55	36.62	3.40	81.65	102.06	108.87	136.08
8	0.1640	4.17	33.57	3.12	74.85	93.56	99.80	124.75
9	0.1495	3.80	30.52	2.84	68.05	85.06	90.73	113.42
10	0.1345	3.42	27.46	2.55	61.23	76.53	81.64	102.04
1/8"	0.1250	3.18	24.92	2.31	55.56	69.45	74.08	92.60
11	0.1196	3.04	24.41	2.27	54.43	68.03	72.57	90.71
12	0.1046	2.66	21.36	1.98	47.63	59.53	63.50	79.38
13	0.0897	2.28	18.30	1.70	40.80	51.00	54.40	68.00
14	0.0747	1.90	15.26	1.42	34.02	42.53	45.37	56.71
15	0.0673	1.71	13.42	1.25	29.91	37.39	39.88	49.85
16	0.0598	1.52	12.20	1.13	27.20	34.00	36.27	45.34
17	0.0538	1.37	10.72	1.00	23.91	29.89	31.88	39.85
18	0.0478	1.21	9.76	0.91	21.76	27.20	29.02	36.27
19	0.0418	1.06	8.33	0.77	18.58	23.22	24.77	30.96
20	0.0359	0.91	7.32	0.68	16.32	20.40	21.76	27.20
21	0.0329	0.84	6.56	0.61	14.62	18.28	19.50	24.37
22	0.0299	0.76	6.10	0.57	13.60	17.00	18.13	22.67
23	0.0269	0.68	5.36	0.50	11.96	14.95	15.94	19.93
24	0.0239	0.61	4.88	0.45	10.88	13.60	14.51	18.13
25	0.0209	0.53	4.17	0.39	9.29	11.61	12.39	15.48
26	0.0179	0.45	3.66	0.34	8.16	10.20	10.88	13.60
27	0.0164	0.42	3.27	0.30	7.29	9.11	9.72	12.15
28	0.0149	0.38	3.05	0.28	6.80	8.50	9.07	11.33

LÁMINA HOJA

Acero cortado en hoja proveniente de rollo, se lámina en frío y caliente, cuenta con múltiples usos de acuerdo a su calibre, ancho y laminación, los anchos comunes son 3' y 4' y largos de 8' y 10', calibres desde 28" a 1/2".

